



INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(51) International Patent Classification ⁶: C08L 23/10	A1	(11) International Publication Number: WO 96/11983 (43) International Publication Date: 25 April 1996 (25.04.96)
(21) International Application Number: PCT/US95/13538 (22) International Filing Date: 16 October 1995 (16.10.95) (30) Priority Data: 08/324,287 14 October 1994 (14.10.94) US (71) Applicant: EXXON CHEMICAL PATENTS INC. [US/US]; 5200 Bayway Drive, Baytown, TX 77520 (US). (72) Inventors: HARRINGTON, Bruce, Allan; 14239 Oak Chase Drive, Houston, TX 77062 (US). BRANT, Patrick; 103 Harborcrest, Seabrook, TX 77586 (US). DIAS, Anthony, Jay; 1411 Quiet Green Court, Houston, TX 77062 (US). (74) Agents: MULLER, William, G. et al.; Exxon Chemical Company, P.O. Box 2149, Baytown, TX 77522-2149 (US).		(81) Designated States: CA, JP, European patent (AT, BE, CH, DE, DK, ES, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE). Published <i>With international search report.</i> <i>Before the expiration of the time limit for amending the claims and to be republished in the event of the receipt of amendments.</i>
(54) Title: BLENDS OF POLYPROPYLENE AND ELASTIC ALPHA-OLEFIN/CYCLIC OLEFIN COPOLYMERS (57) Abstract Blends of semi-crystalline polymers with rubbery thermoplastic copolymers are provided. The rubbery thermoplastic copolymers are elastic at temperatures above their T _g 's and properties similar to thermoplastic elastomers and surface tensions 5 dynes/cm or more different, preferably greater than the surface tension of the semi-crystalline polymer. Improved properties include good elastic recovery, toughness, and high elasticity without significant loss in optical properties.		

FOR THE PURPOSES OF INFORMATION ONLY

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AT	Austria	GB	United Kingdom	MR	Mauritania
AU	Australia	GE	Georgia	MW	Malawi
BB	Barbados	GN	Guinea	NE	Niger
BE	Belgium	GR	Greece	NL	Netherlands
BF	Burkina Faso	HU	Hungary	NO	Norway
BG	Bulgaria	IE	Ireland	NZ	New Zealand
BJ	Benin	IT	Italy	PL	Poland
BR	Brazil	JP	Japan	PT	Portugal
BY	Belarus	KE	Kenya	RO	Romania
CA	Canada	KG	Kyrgyzstan	RU	Russian Federation
CF	Central African Republic	KP	Democratic People's Republic of Korea	SD	Sudan
CG	Congo	KR	Republic of Korea	SE	Sweden
CH	Switzerland	KZ	Kazakhstan	SI	Slovenia
CI	Côte d'Ivoire	LI	Liechtenstein	SK	Slovakia
CM	Cameroon	LK	Sri Lanka	SN	Senegal
CN	China	LU	Luxembourg	TD	Chad
CS	Czechoslovakia	LV	Latvia	TG	Togo
CZ	Czech Republic	MC	Monaco	TJ	Tajikistan
DE	Germany	MD	Republic of Moldova	TT	Trinidad and Tobago
DK	Denmark	MG	Madagascar	UA	Ukraine
ES	Spain	ML	Mali	US	United States of America
FI	Finland	MN	Mongolia	UZ	Uzbekistan
FR	France			VN	Viet Nam
GA	Gabon				

- 1 -

**BLENDS OF POLYPROPYLENE AND ELASTIC ALPHA-
OLEFIN/CYCLIC OLEFIN COPOLYMERS**

FIELD OF THE INVENTION

5 This invention relates to blends of crystalline or semi-crystalline polymers, such as polypropylene, with predominantly amorphous, elastomeric copolymers that have a packing length greater than that of the host polymer. These copolymers, when blended with semi-crystalline homopolymers such as polypropylene act to toughen the homopolymer without detrimentally affecting the surface properties of
10 the semi-crystalline homopolymer.

BACKGROUND OF THE INVENTION

15 Semi-crystalline polymers such as polypropylene are versatile polymers useful in many applications since their crystallinity imparts desirable mechanical properties such as stiffness. They suffer however from brittleness in certain applications. One of the methods used to reduce the brittleness of semi-crystalline polymers is to blend them with low glass transition temperature (T_g) elastomers such as ethylene-propylene rubber or ethylene-propylene-diene modified
20 terpolymers (EPRs and EPDMs). These blends are less brittle and provide an improved impact resistance, however they often suffer from reduced gloss, haze, and poor tactile quality, as well as decreased flexural modulus when these properties are compared to the original semi-crystalline homopolymer. One reason for this loss of surface properties has to do with chain flexibility. Both the semi-
25 crystalline polymers and the rubber copolymers that are blended with them comprise very flexible chains. They have similar packing lengths as defined and disclosed in Fetters, L. J., Lohse, D. J., Richter, D., Witten, T. A., and Zirkel, A. Macromolecules, 1994, and Brant, P., Karim, A., Sikka, M., and Bates, F.S., J. Poly. Sci., Poly. Phys. Ed. 1994, incorporated by reference herein. Because of their
30 similar flexibility and packing lengths, both polymers can reside at interfaces and surfaces with similar ease, i.e. when the chains come to an interface or surface, they can fold themselves to fit along the surface, or fold themselves to return to the bulk of the polymer without much trouble. Hence, there exists a roughly equal probability that both the rubber polymer (rubber phase) and the semi-crystalline
35 polymer (continuous phase) of the blend can reside at the surface. In turn, two

- 2 -

phases on the surface of a polymer contributes to a decrease in gloss and an increase in haze. Therefore, there exists a need in the art to provide blends of semi-crystalline polymers with impact modifying rubbers that achieve a balance of useful mechanical properties and desirable surface properties.

5

SUMMARY OF THE INVENTION

In accordance with the present invention, blends comprising a semi-crystalline polymer and a rubbery thermoplastic copolymer having good strength and surface properties without significant loss of optical or tensile properties are provided.

10

BRIEF DESCRIPTION OF THE DRAWINGS

Figure 1 is a plot of 1% Secant Flexural Modulus vs. 23 °C Garner Impact for neat polypropylene and blends P, Q, R and S.

15

DETAILED DESCRIPTION OF THE INVENTION

The present invention relates to blends of a semi-crystalline polymer, such as polypropylene, with a rubbery copolymer with a significantly different surface tension, preferably a difference of 3 dynes per centimeter or more. In a preferred embodiment the rubbery thermoplastic copolymer has a surface tension 3 or more dynes/cm greater than the surface tension of the semi-crystalline polymer, even more preferably 5 dynes/cm greater, even more preferably 8 dynes/cm greater, even more preferably 10 dynes/cm greater. These blends have superior strength, haze and gloss properties, among others. In particular these blends have increased impact resistance without a significant reduction in flexural modulus and gloss.

20
25

Hereinafter the use of the term polypropylene is merely exemplary, and is not intended to limit the scope of the invention in any way. Those of ordinary skill in the art will recognize that other semi-crystalline polymers comprising C₂ to C₄₀ α -olefins would be used in a similar fashion.

30

In one set of embodiments the rubbery thermoplastic copolymer is typically present in the blend in amounts of up to about 90 weight %, preferably up to about

35

- 3 -

70 weight %, even more preferably up to about 50 weight % with the balance being made up of the semi-crystalline polymer. (wt% is based upon the weight of the blend) In an alternate set of preferred embodiments the rubbery thermoplastic copolymer is present at about 0.5 to about 45 wt%, even more preferably 1 to about 30 wt%, even more preferably about 10 to about 25 wt%, with the balance being made up by the semi-crystalline polymer.

Preferred semi-crystalline polymers that may be blended or combined with the rubbery copolymers include propylene homopolymers and copolymers. The homopolymers preferably have about 95% or more heptane insolubles, more preferably about 97% or more heptane insolubles (Insolubles measured on bulk polymer samples dried at 100 °C in a vacuum oven prior to boiling in n-heptane for 1.5 hours. Thereafter samples are vacuum dried, rinsed with acetone, dried further in a vacuum oven at 100 °C and thereafter heated in a muffle furnace for 8 hours at 1100 °F (593 °C). Heptane insolubles = $100 \times (\text{weight of sample after heating in muffle furnace} / \text{weight of the sample prior to combining with n-heptane})$.) The copolymers may be copolymers of propylene with any aliphatic or aromatic cyclic or branched olefin, preferably ethylene or any C₄ to C₁₀₀ α -olefin, preferably ethylene or any C₄ to C₂₀ α -olefin. For the purposes of this invention ethylene is considered an α -olefin. Such propylene copolymers and homopolymers are well known in the art and are commercially available under many trade names.

Rubbery copolymers with lower flexibility can be made by incorporating rigid or bulky comonomers into the polymer chains. For example the rubbery copolymer can be an α -olefin, preferably ethylene or propylene, with a cyclic olefin, preferably norbornene and the like, or styrene or the like. Preferred rubbery thermoplastic copolymers and methods to make them are disclosed and claimed in United States Patent Application 08/005,676, filed 1-19-93 (now published as WO 9417113, pub. August 11, 1994), which is incorporated by reference herein. Preferred rubbery thermoplastic copolymers of an α -olefin and a cyclic olefin which are blended with the polypropylene described above are preferably copolymers which can be made, for example, by polymerizing cyclic olefin comonomers with one or more α -olefins in the presence of a coordination catalyst, preferably a single site catalyst. Preferred rubbery thermoplastic copolymers generally comprise from about 5 to about 30 mole percent of the cyclic comonomer, preferably from about 10 to about 20 mole percent of the cyclic comonomer. Preferred rubbery

- 4 -

thermoplastic copolymers have a high molecular weight up to 2,000,000 or more, preferably from about 30,000 to about 1,000,000, even more preferably from about 50,000 to about 500,000, even more preferably 80,000 to about 250,000. (As used herein, molecular weight refers to the weight average molecular weight (M_w) unless otherwise indicated.) In preferred embodiments the rubbery thermoplastic copolymers may have a relatively narrow molecular weight distribution (MWD), i.e. (M_w/M_n) of less than about 4, preferably less than about 2. The rubbery thermoplastic copolymers generally have a glass transition temperature (T_g) in the range of -50°C to 50°C, preferably -15°C to about 25°C. As used herein, T_g is determined by differential scanning calorimetry (DSC) under ASTM E 1356.

The rubbery copolymers also have a number of unusual properties which make them rather desirable for blends with polypropylene and other semi-crystalline copolymer, such as toughness and optical clarity combined with elasticity and good recovery after elongation. (As used herein, ultimate tensile strength, elongation at break, and recovery are determined at 25°C using procedures in accordance with ASTM D-412, unless otherwise noted.)

In addition to having a long statistical chain segment length, the preferred rubbery thermoplastic copolymers have:

- 1) an elongation at break of 300% or more and especially of 400% or more;
- 2) a tensile strength at 150% elongation of at least 800 psi (5.5 MPa), preferably at about 1000 psi (6.8 MPa);
- 3) an elastic recovery of at least 70% after 10 minutes relaxation from 150% elongation, more preferably recovery of at least 80%;
- 4) an ultimate tensile strength of at least 2500 psi (17.2 MPa), more preferably above 3500 psi (24.1 MPa) and/or
- 5) a surface tension of about 33 dynes/cm or more, preferably about 37 dynes/cm or more.

- 5 -

The rubbery copolymers described above are also unique in that they remain elastic well above their glass transition temperatures and remain ductile well below their T_g . In general, the copolymer remains rubbery at temperatures above the approximate T_g (as measured by DSC) of the copolymer, for example, from the T_g (-50°C to 50°C) to above 100°C, preferably above 150°C. In another preferred embodiment the rubbery copolymer is elastic over the temperature range of from its T_g to 100°C above its T_g , preferably over the range of from its T_g to 150°C above its T_g . This unusual elasticity may also be reflected by a rubbery storage modulus over this temperature range. The rubbery storage modulus of the copolymers is readily observed as a plateau between about 1 and about 100 MPa by dynamic mechanical thermal analysis (DMTA) at a frequency of 1 or 10 Hz with a 2°C/min temperature ramp using commercially available DMTA equipment, for example, from Polymer Laboratories, Inc. The ductile-brittle transition can be measured by ASTM D-746 and although the rubbery thermoplastic copolymers may have a T_g of -5 °C to 5 °C as measured by DSC, they remain ductile to temperature below -20 °C, and even to temperatures below -30 °C.

If desired, the rubbery modulus can be extended to higher or lower temperatures by the optional use of crosslinking, plasticizing additives, or a combination of crosslinking and plasticizers. In general, plasticizers tend to lower the temperature at which the copolymer becomes brittle, while crosslinking raises the temperature at which the copolymer will flow or otherwise suffer a significant reduction in strength.

Surface tension is measured by using standard treat solutions well known in the art (ASTM D2578-94). ASTM D2578-94 is hereby incorporated by reference. A typical Ethylene-norbornene copolymer having about 10 mol% norbornene has a surface tension of about 41 dynes/cm and typical polypropylene has a surface tension of about 30 or 31 dynes/cm.

The α -olefin(s) which are copolymerized with the cyclic olefin(s) to make the rubbery thermoplastic copolymer can be any unsaturated, copolymerizable monomer having at least 2 carbon atoms, or mixture or combination thereof. Typically, the α -olefin is a substituted or unsubstituted C_2 - C_{20} α -olefin, such as, for example, ethylene, propylene, 1-butene, 1-pentene, 3-methyl-pentene-1, 4-methylpentene-1, 1-hexene, 1-heptene, 1-octene, 1-nonene, 1-decene, 1-undecene,

- 6 -

1-dodecene, 1-tetradecene, 1-hexadecene, 1-octadecene, 1-eicosene, 3,5,5-trimethylhexene-1, allyltrimethyl silane, and the like; or vinyl aromatic and alicyclic monomers, such as, for example, styrene, alkyl-substituted styrene, vinyl cyclohexene, and the like. The α -olefin can also be (or include) a longer α -olefin (having 10 or more carbon atoms), a branched α -olefin or a polyene, or a combination thereof, either alone as the sole α -olefin comonomer(s), or more preferably as a termonomer in combination with a C_2 - C_{20} α -olefin, particularly a C_2 - C_8 α -olefin, especially ethylene, propylene or a mixture of ethylene and propylene. (As used herein the term " α -olefin" or "alpha-olefin" is intended to refer generically to longer α -olefins, branched α -olefins, and polyenes, as well as the more usual C_2 - C_{20} α -olefins. Also as used herein the term copolymer is intended to refer to polymers of two or more different monomers.)

In general, any cyclic olefin can be copolymerized with the α -olefin to produce the rubbery copolymer provided the cyclic olefin includes cyclized ethylenic or acetylenic unsaturation or ethylenic or acetylenic unsaturation pendant to the cyclic structure as in styrene or vinylcyclohexane, said unsaturation which undergoes addition polymerization in the presence of the catalyst (substantially without ring opening) so that the ring structure in which the unsaturation is present is incorporated into the polymer backbone. A method to prepare the rubbery copolymers and lengthy list of preferred cyclic monomers is disclosed in PCT publication WO/9417113, published August 11, 1994, and incorporated by reference herein.

Especially preferred cyclic olefins include cyclobutene, cyclopentene, deltaxylene, norbornene, methylnorbornene, tetracyclododecene, methyltetracyclododecene, dimethyltetracyclododecene, tricyclo(4.3.0.1^{2,5})-3-decene, and pentacyclo(4.7.0.1^{2,5}.0^{8,13}.1^{9,12}). Of these, norbornene is preferred for its ready commercial availability and effectiveness.

Polyenes having two or more double bonds can optionally be used in a relatively minor proportion to impart higher molecular weight to the copolymer and/or provide residual pendant side chain unsaturation for functionalization or crosslinking. Where the polyenes can participate in polymerization at two (or more) sites, these monomers tend to promote chain extension which can double or quadruple the molecular weight at low incorporation rates, and also raise the upper

- 7 -

temperature at which the rubbery storage modulus plateau is present. Ideally the polyene is not present in such high amounts which might result in excessive crosslinking and produce insoluble gel formation. Preferably, the molecular weight is suitably increased by including the optional polyene in the copolymer at from 0.5 to 3 mole percent.

Suitable polyenes include, for example, α,ω -dienes having from 5 to 18 carbon atoms, such as 1,4-pentadiene, 1,5-hexadiene, 1,6-heptadiene, 1,7-octadiene, 1,8-nonadiene, 1,9-decadiene, 1,10-undecadiene, 1,11-dodecadiene, 1,12-tridecadiene, 1,13-tetradecadiene, 1,14-pentadecadiene, 1,15-hexadecadiene, 1,16-heptadecadiene, 1,17-octadecadiene, or the like.

When two (or more) of the double bonds are sufficiently reactive under the particular reaction conditions to participate in the polymerization reaction, suitable optional polyenes generally also include other linear or branched aliphatic dienes and trienes, monocyclic dienes and trienes, bicyclic dienes and trienes, polycyclic dienes, aromatic dienes, and the like. Specific representative examples of non-conjugated polyenes include 1,4-hexadiene, 6-methyl-1,4-heptadiene, 4-isopropyl-1,4-hexadiene, 4-methyl-1,4-hexadiene, 5-methyl-1,4-hexadiene, 4-ethyl-1,4-hexadiene, 4-isopropyl-1,4-hexadiene, 6-phenyl-4-propyl-1,4-hexadiene, 4,5-dimethyl-1,4-hexadiene, 6-phenyl-1,4-hexadiene, 5-methyl-1,5-octadiene, 6-methyl-1,5-octadiene, 6-methyl-1,5-heptadiene, 5,7-dimethyl-1,5-octadiene, 4,5-dipropyl-1,4-octadiene, 5-propyl-6-methyl-1,5-heptadiene, 5-ethyl-7-methyl-1,6-octadiene, 1,5-hexadiene, 1,6-heptadiene, 1,6-octadiene, 1,7-octadiene, 1,8-nonadiene, 1,8-decadiene, 1,9-decadiene, and 1,10-undecadiene; dicyclopentadiene, tricyclopentadiene, 1-vinyl-4-(1-propenyl)-cyclohexane, 4-methylcyclo-1,4-octadiene, 4-methyl-5-propylcyclo-1,4-octadiene, 5-methylcyclopentadiene, 4-methyl-5-ethyldicyclopentadiene, 5-isopropyldicyclopentadiene, 1,5,9-cyclododecatriene, 4-(1-butenyl-2)-styrene, 4-2-butene-2-yl)-styrene and trans-1,2-divinylcyclobutane, 5-ethylidenenorbornene-2, 5-propylidenenorbornene-2, 5-butylidenenorbornene-2, 5-isopropylidene-norbornene-2, 2-methyl-2,5-norbornadiene, 5-methyl-2,5-norbornadiene, 2-propyl-2,5-norbornadiene, 5-methylene-2-norbornene, 5-(2-butenyl)-2-norbornene, 3-heptyl-2,5-norbornadiene, 2-ethyl-3-propyl-2,5-norbornadiene, 2-(1',5'-dimethylhexene-4-yl)-2,5-norbornadiene, dicyclopentadiene,

- 8 -

- 5-isopropylidicyclopentadiene, 5-isopropylidene-bicyclo(2.2.2)octene-2,
 5-ethylidenebicyclo(2.2.2)octene-2, 5-butyldenebicyclo(2.2.2)octene-2, 2-
 ethylbicyclo(2.2.2)octadiene-2,5, 2-methyl-3-ethyl-bicyclo(2.2.2)octadiene-2,5, 2-
 hexylbicyclo(2.2.2)octadiene-2,5, 2-(1',5'-dimethylhexenyl-
 5 4)bicyclo(2.2.2)octadiene-2,5, 1-isopropylidenebicyclo(4.4.0)decadiene-2,6, 2-
 isopropylidenebicyclo(4.4.0)decene-6, 2-ethylidene-bicyclo(4.4.0)decene-6, 3-
 ethylidenebicyclo(3.2.0)heptadiene-2,6, 3-methylbicyclo(3.3.0)octadiene-2,6, 3-
 methyltetrahydroindene,
 6-methyltrahydroindene,
 10 2-propyltetrahydroindene,
 1-isopropylidenetetrahydroindene,
 1-(1'-phenyl)-ethylidenetetrahydroindene and the like.

- In a preferred embodiment, the polymerization methodology is practiced in
 15 the manner and with the catalyst systems referred to, disclosed, and described in the
 following references: US 5,055,438; US 5,507,475; 5,096,867; WO 92 00333; US
 5,264,405; US 5,324,800; CA 1,268,753; US 5,017,714; 5,240,894; US 5,198,401;
 US 5,153,157; WO 94 03506; EPA 520,732, pub 12-30-92; EPA 129,368, pub. 12-
 27-84; and EPA 277,003 & 277,004, pub. 6-3-88, which are hereby incorporated
 20 herein by reference.

- Generally, the preferred catalyst systems employed in preparing the
 copolymer of the invention can comprise a complex formed upon admixture of a
 Group 4 transition metal component with an activating component. The catalyst
 25 system can be prepared by addition of the requisite transition metal and alumoxane
 components, or a previously cationically activated transition metal component, to an
 inert solvent in which olefin polymerization can be carried out by a solution, slurry
 or bulk phase polymerization procedure.

- Optimum results are generally obtained when the Group 4 transition metal
 30 compound is present in the polymerization diluent, in a concentration of preferably
 from about 0.00001 to about 10.0 millimoles/liter of diluent and the activating
 component is present in an amount to provide a molar activating component to
 transition metal ratio of from about 0.5:1 to about 2:1 or more, and in the case of
 35 alumoxane, the molar alumoxane to transition metal can be as high as 20,000:1.

- 9 -

Sufficient solvent is normally used so as to provide adequate heat transfer away from the catalyst components during reaction and to permit good mixing.

5 The catalyst system ingredients, that is, the transition metal, the alumoxane and/or ionic activators, and polymerization diluent can be added to the reaction vessel rapidly or slowly. The temperature maintained during the contact of the catalyst components can vary widely, such as, for example, from -100°C to 300°C. Greater or lesser temperatures can also be employed. Preferably, during formation of the catalyst system, the reaction is maintained within a temperature of from about 10 25°C to 100°C, most preferably about 25°C.

 In a preferred embodiment, the catalyst system is utilized in the liquid phase (slurry, solution, suspension or bulk phase or combination thereof), high pressure fluid phase or gas phase (where the α -olefin and cyclic olefin are sufficiently 15 volatile, e.g. up to C₈) for copolymerization of α -olefin and cyclic olefin. These processes may be employed singularly or in series. The liquid phase process comprises the steps of contacting α -olefin and cyclic olefin with the catalyst system in a suitable polymerization diluent and reacting said monomers in the presence of said catalyst system for a time and at a temperature sufficient to produce a 20 copolymer of high molecular weight. Conditions most preferred for the copolymerization of α -olefin are those wherein α -olefin is submitted to the reaction zone at pressures of from about 0.019 psi (.1 KPa) to about 50,000 psi (345 MPa) and the reaction temperature is maintained at from about -100°C to about 300°C. The reaction time is preferably from about 10 seconds to about 4 hours.

25 One example of polymerization for production of the α -olefin/cyclic olefin copolymer is as follows: in a clean, dry and purged stirred-tank reactor containing solvent and optional scavenger, liquid comonomer is introduced, such as 2-norbornene. The catalyst system is introduced via nozzles in either the vapor or 30 liquid phase. Feed ethylene (or other olefin) gas is introduced either into the vapor phase of the reactor, or sparged into the liquid phase as is well known in the art. The reactor contains a liquid phase composed substantially of solvent, liquid comonomer, together with dissolved ethylene gas, and a vapor phase containing vapors of all monomers. The reactor temperature and pressure may be controlled 35 via reflux of vaporizing comonomer (autorefrigeration), as well as by cooling coils, jackets etc. The polymerization rate is generally controlled by the concentration of

- 10 -

catalyst. The ethylene and comonomer contents of the polymer product are determined by NMR and manipulating the ratio of ethylene to comonomer in the reactor.

5 Alternatively, the α -olefin/cyclic olefin copolymer can be prepared by a high pressure process. The high pressure polymerization is completed at a temperature from about 105°C to about 350°C, preferably from about 120°C to about 250°C, and at a pressure of from about 100 bar to about 3200 bar, preferably from about 200 bar (20 MPa) to about 1300 bar (130 MPa), in a tubular or stirred autoclave
10 reactor. After polymerization and catalyst deactivation, the product copolymer can be recovered using conventional equipment for polymer recovery, such as, for example, a series of high and low pressure separators wherein unreacted α -olefin, and unreacted cyclic olefin in some instances, particularly when the comonomer is relatively volatile, can be flashed off for recycle to the reactor and the polymer
15 obtained extruded in an underwater pelletizer. An advantage of the high pressure process is that the flashing off of the cyclic olefin is relatively effective, particularly at the ratio of cyclic olefin: α -olefin used in the copolymerization to obtain the desired comonomer incorporation in the copolymer. Pigments, antioxidants and other known additives and fillers, as are known in the art, can be added to the
20 polymer.

 The copolymerization process can be a continuous or batch reaction. Typically, the continuous process, where reactants are continuously fed to the reactor and product continuously withdrawn, is preferred in commercial production
25 facilities for economic reasons. The continuous process also has the advantage of promoting more uniform comonomer incorporation into the polymer.

 As before noted, any suitable coordination catalyst system can be used. Preferably, however, the catalyst system has the ability to incorporate a relatively
30 high content of the comonomer. The catalyst preferably has a relatively low α -olefin:cyclic olefin reactivity ratio less than about 300, more preferably less than 100, and especially from about 25 to about 75. Accordingly, the selection of the transition metal component, and other catalyst system components, is another parameter which may be utilized as a control over the α -olefin content of a
35 copolymer with a reasonable ratio of α -olefin to cyclic olefin feed rates.

Preferred catalyst systems include:

- 11 -

- Cp₂ZrMe₂ combined with DMAH B(pfp₄);
 Cp₂ZrCl₂ combined with MAO;
 Cp₂HfMe₂ combined with DMAH B(pfp₄);
 5 Cp₂HfCl₂ combined with MAO;
 Me₂Si bis(Ind)HfMe₂ combined with DMAH B(pfp₄);
 Me₂Si bis(Ind)HfCl₂ combined with MAO;
 Dimethylsilyl(tetramethyl-cyclopentadienyl) (amidocyclododecyl) titanium
 dichloride combined with MAO;
 10 Dimethylsilyl(tetramethyl-cyclopentadienyl) (amidocyclododecyl) titanium
 dichloride combined with DMAH B(pfp₄);
 Me₂Si(H₄Ind)ZrCl₂ combined with MAO; and
 Me₂Si(H₄Ind)ZrMe₂ combined with DMAH B(pfp₄).
 15 Abbreviations: Cp =cyclopentadienyl, Me = methyl, DMAH B(pfp₄) =
 dimethylanilinium tetra(perfluorophenyl) borate, MAO = methylalumoxane, and Ind
 = indenyl.

- In a preferred embodiment rubbery α -olefin/cyclic olefin copolymer
 20 (preferably an ethylene/norbornene copolymer) would be polymerized by the
 following procedure: A 1-liter or 2-liter autoclave reactor equipped with a paddle
 stirrer, an external water or steam jacket for temperature control, a regulated supply
 of dry nitrogen, ethylene, propylene, toluene and hexane, and a septum inlet for
 introduction of comonomer, transition metal compound, co-catalyst and scavenger
 25 solutions would be dried and purged thoroughly prior to use. Optionally solvent, if
 used, would be introduced to the reactor (typically toluene or hex). A quantity of
 cyclic olefin (typically in toluene or a hexanes solvent), optionally a scavenger
 would be added by cannula (typically an AlR₃, preferably TEAL or TIBA, most
 preferably TIBA) and the ethylene or propylene monomer (as a liquid or gas) would
 30 be introduced into the reactor. The reactor would then heated to between 30°C -
 80°C and a toluene solution of the transition metal compound, previously activated
 by the co-catalyst, will be introduced into the system by cannula using high pressure
 nitrogen or solvent. The polymerization reaction would be generally conducted for
 10 to 120 minutes. The reaction will be halted by rapidly cooling and venting the
 35 system. The resulting polymer would be recovered by precipitation in methanol

- 12 -

and/or isopropanol, filtration and drying the polymer *in vacuo* for about 12-48 hours at ambient temperature up to 100°C.

Scavengers, when used, would be 2.0 molar solutions of triisobutyl aluminum (TIBA), trimethyl aluminum (TMA), diisobutyl aluminum (DiBAL) or triethyl aluminum (TEA). Possible transition metal compounds include dimethylsilyl bis(indenyl) hafnium dimethyl, dimethylsilyl(tetramethyl-cyclopentadienyl) (amidocyclododecyl) titanium dichloride, bis(cyclopentadienyl) zirconium dimethyl or dimethylsilyl bis(tetrahydroindenyl) zirconium dichloride.

10

The blends, including the cured blends discussed below, produced herein are useful in any application where rubber toughened polypropylene has been used in the past. For example the blend may be molded, blown, cast, extruded or otherwise formed into articles. Examples include automotive trim, automotive bumpers, packages, containers, films, sheets, strips and the like.

15

EXAMPLES

Ethylene/norbornene copolymer (ENB1) was produced according to the following procedure:

20

About 15.5 g norbornene dissolved in 400 ml hexanes were added to a one liter Zipperclave reactor equipped with a paddle stirrer, an external water or steam jacket for temperature control; a regulated supply of dry nitrogen, ethylene, propylene, toluene and hexane; and a septum inlet for introduction of comonomer, transition metal compound, co-catalyst and scavenger solutions the reactor was dried and purged thoroughly prior to use. Ethylene was introduced at a pressure of 50.0 psig (345 kPa) and the reactor was heated (30°C) and stirred. 23.0 mg of the bis(cyclopentadienyl) zirconium dimethyl (a molar excess) and 9.6mg of dimethylanilinium tetra(perfluorophenyl)borate were mixed in toluene (2-3 ml) and left to activate for 10 minutes. This two-phase oil/toluene mixture was sealed in a vial with septa, the vial was connected to the reactor via cannula and then pressurized with N₂ in the reactor. The polymerization reaction was conducted for 19 minutes, yielding 3.91 g of copolymer. ENB2 and ENB3, were made following the procedure above except for the differing conditions noted in Table 1 which reports the polymerization and some physical data.

25

30

35

- 13 -

Table 1. Rubbery Ethylene/Norbornene Copolymer Data

	ENB1	ENB2	ENB3	ENB4
Cp ₂ ZrMe ₂ (mg)	23	16	42	V
DMAH B(pfp ₄) (mg)	9.6	20	48	V
Temp (°C)	40	50	40	40
C ₂ (psi/kPa)	50/345	36/248	38.8/268	35/241
Norbornene	15.5g	38.8g	38.8g	40g
Time (hr)	0.33	0.33	0.25	V
Yield(g)	3.91	52.0	NA	V
Act.(g/g-h)	24,300	25,00	NA	V
Mw	67,000	110,000	150,000	72,000
Mol%NB*	11.9	11.7	8.7	14.0
Stress@ (psi/MPa)	3140/22	NA	NA	3840/26
Elong.# (%)	535	NA	NA	443

Elong.# = elongation at break as measured by ASTM 412.

5 Stress@ = stress at maximum load as measured by ASTM 412.

Mol%NB = mole percent of norbornene in the polymer as measured by ¹³CNMR and/ or ¹HNMR.

V - Variable. ENB4 was a composite blend of many small batch runs. The values given are for the final blended material.

10 ENB5 is ENB4 with a stabilizer package of IRGAPHOS 168™ (750 ppm) and IRGANOX 1076™ (1500 ppm) added.

NA - Data Not available.

Several polypropylenes were made or purchased. These were:

15

(1) PP1 - high crystallinity, brittle, isotactic PP (98.7% heptane insolubles) made using a supported TiCl₄/MgCl catalyst activated with a methylcyclohexyldimethoxysilane donor in typical commercial slurry conditions.

20

(2) PP2 - a commercially available isotactic PP homopolymer sold under the trade name ESCORENE PP1012™ by Exxon Chemical Company having a melt flow rate of 5.0 g/10 min (ASTM D 1238-65T condition L);

- 14 -

(3) PP3 - a commercially available polypropylene homopolymer sold under the trade name Escorene PD 3345E from Exxon Chemical Company, having a melting point of 165 °C and a melt flow rate of 35 g/10 min (ASTM D 1238-65T condition L);

5

(4) PP4 - a commercially available polypropylene homopolymer sold under the trade name Escorene PD 4193 from Exxon Chemical Company, having a melt flow rate of 7.3 g/10 min (ASTM D 1238-65T condition L); and

10

(5) PP5 - a low melt flow rate (MFR) atactic PP made by polymerizing propylene in the presence of $\text{Me}_2\text{Si}[\text{Me}_4\text{CpN}(\text{C}_{12}\text{H}_{23})]\text{TiCl}_2$ and methylalumoxane in solution conditions.

EXAMPLE 2

15

Several blends, A-H, were physically mixed using a Brabender Counter rotating mixer using the small mixing head (45ml). Mixing conditions were as follows:

20

The head was preheated to 190°C for 5 minutes. A manually blended mixture was fed into the mixing chamber with screws rotating at 60 rpm. The mixture was blended for 5 minutes and then removed. The blends were then compression molded. The blends and the test data are reported in Table 2.

25

Several blends (M-T) were mixed and pelletized using two passes through a single screw extruder with a 200 mesh screen pack. The pellets were injection molded into test pieces.

- 15 -

Table 2

Blend	PP (g)	ENB (g)	wt. % rubber
A	PP5(0.032)	ENB1(0.6)	95%
B	PP5(0.07)	ENB1(0.6)	90%
C	PP5(0.106)	ENB1(0.6)	85%
D	PP5(0.4)	ENB1(0.6)	60%
E	PP5(0.6)	ENB1(0.6)	50%
F	PP3 (36.31)	ENB2 (90.4)	20%
G	PP3 (27.15)	ENB2 (18.14)	40%
H	PP4(34.92)	ENB3(11.64)	25%
M*	PP1(10lbs)	none	4%
N*	PP1 (9.6lbs)	ENB5 (181.6g)	4%
O*	PP1 (9.6lbs)	VISTALON457™(181.6g)	4%
P	PP2(9.6lbs)	ENB5(181.6g)	4%
Q	PP2(9.6lbs)	Vistalon719™(181.6g)	4%
R	PP2(9.6lbs)	Vistalon404™(181.6g)	4%
S	PP2(9.6lbs)	Vistalon457™(181.6g)	4%
T	PP2 (10 lbs)	---none	4%

* = 550ppm of BHT and 800ppm of calcium stearate were added as a stabilizing package.

5

The copolymers were selectively tested for norbornene content by carbon nuclear magnetic resonance (CNMR) and/or proton NMR (^1H NMR); molecular weight (M_w) and molecular weight distribution (M_w/M_n) by gel permeation chromatography; and glass transition temperature (T_g) by differential scanning calorimetry (DSC) using ASTM E 1356. The DMTA was done on a Polymer Laboratories, Inc. DMTA apparatus using a single cantilever head and a 2°C/min. temperature ramp according to the manufacturer's recommended procedures at 1 Hz and 10 Hz from -120°C to 150°C. Physical properties such as tensile strength at break; elongation at break; tensile strength at 150% strain; and recovery (100 minus tension set) were measured according to ASTM 638. Physical properties were measured on an Instron tensile testing apparatus at 4 in./min. (200%/min.), and the recovery data at 20 in./min. (1000%/min.). Testing was at ambient conditions unless otherwise indicated. Y ungs m dulus and yield stress were measured by a

10

15

- 16 -

ASTM 638. Flexural strength was measured by ASTM 638. 1 % Secant flexural modulus was measured by ASTM D 790. Gardner impact was measured by ASTM D 5420. T_m was measured by DSC, second melt. Mold shrinkage is measured by ASTM D 955. 60° gloss is measured by ASTM 2457.

5

The blends were injection molded into plaques and tested for tensile at break, elongation at break, yield stress, Young's Modulus, flex strength, 1 % Secant flexural modulus, Gardner Impact at 23°C, melting point(T_m), crystallization temperature(T_c), mold shrinkage and 60° gloss. The results are presented in Table

10 3a and 3b.

- 17 -

Table 3a

Blend	Tensile at break (psi/MPa)	Elong. at break (%)	Yield stress (psi/MPa)	Young's modulus (psi/MPa)	Flex Strength (psi/MPa)
M	3491/24.0	730	5189/35.7	109723/756.5	7164/49.3
N	3193/22.0	656	5041/34.7	109889/757.6	6963/48.0
O	3018/20.8	771	4758/32.8	98296/677.7	6409/44.1
P	3233/22.2	889	4712/32.4	91651/631.9	5855/40.4
Q	2759/19.0	817	4529/31.2	70965/489.3	5652/38.9
R	3143/21.6	928	4437/30.5	83668/576.8	5383/37.1
S	3093/21.3	950-NB	4404/30.3	71120/490.3	5476/37.7
T	3337/23.0	950-NB	4794/33.0	88281/608.6	5883/40.5

NB = no break

5

Table 3b

Blend	Secant 1 mod. (psi/MPa)	Gardner impact (in/lbs)	Tm (°C)	Tc (°C)	Mold shrinkage (%)	60° gloss (%)
M	252727/1743	8.2 Br	168/160	114	1.35	87.6
N	247397/1706	61 BrSh	168/160	115	1.36	87.1
O	230029/1586	197 DuSh	168/160	116	1.29	87.0
P	200500/1382	167 DuSh	160	115	1.3	87.4
Q	193079/1331	163 DuSh	161/144	113	1.3	86.9
R	183279/1264	167 Du	166/155	112	1.25	86.7
S	192026/1324	177 Du	166/155	113	1.22	86.8
T	201100/1387	118 DuSh	161.4	120.2	1.21	87.4

Du = ductile, Sh = shatter, Br = brittle.

- 18 -

Izod tests were also conducted according to ASTM D-256. The results are reported in table 4.

Table 4 (Izod impact results in ft-lbs/in (J/cm))

5

Blend	Notched 23°C	Unnotched 23°C	Unnotched -18°C	Unnotched -23°C	Unnotched -40°C
M	0.65/4.4	32.7/225.4	4.0/27.5	3.3/22.7	3.8/26.2
N	0.68/4.6	30.4/209.6	4.5/31.0	3.6/24.8	2.8/19.3
O	0.88/6.0	30.0/206.8	5.7/39.3	4.4/30.3	4.5/31.0
P	0.47/3.2	22.5/155.1	3.1/21.3	2.8/19.3	2.8/19.3
Q	0.60/4.1	30.3/208.9	3.2/22.0	2.7/18.6	3.1/21.3
R	0.70/4.8	30.1/207.5	4.0/27.5	4.4/30.3	3.4/23.4
S	0.74/5.1	30.2/208.2	3.8/26.2	4.2/28.9	3.9/26.8
T	0.66/4.5	27.4/188.9	4.1/28.2	4.0/27.5	3.8/26.2

Blends M through T compared the physical and mechanical properties of two polypropylenes blended with E/NB rubber and different commercial EP rubbers to the non-blended PP. Both rubbers provide significant impact resistance improvement, but the E/NB modified polymers show no loss of tensile strength or flex strength as the EP modified polymers do (Table 3 and 4). In addition there is no loss of surface gloss incurred by adding E/NB rubber as there is when adding EP rubber (Particularly evident with the commercial PP blends P through T). The mold shrinkage results were inconclusive at these rubber levels. The E/NB modified polymers retained low temperature impact properties as measure by the IZOD impact test (Table 4) down to somewhere between -18 and -29 °C but lost impact resistance at -40 °C.

Typically there is an inverse relationship between strength and impact resistance in a blend of semi-crystalline polymer and rubbery copolymer. (As more rubber is added to the semi-crystalline polymer, its impact properties improve, but strength is lost.) This relationship may be represented by a line drawn between the Modulus and Gardner Impact values for homopolypropylene and the values of 160,000 psi Modulus and 320 ft-lbs Gardner Impact. Most of the commercial impact modified PP's have properties that fall on or close to this line. It is

- 19 -

desirable to find impact modifying rubbers that result in values that are above and to the right of this line.

Figure 1 plots 1 % Secant flexural modulus (kpsi) vs. 23 °C Gardner Impact
5 (ft-lb) for five compositions.

Symbol	Description
■	ESCORENE™ 1012 polypropylene
•	Blend P
▲	Blend Q
X	Blend R
Z	Blend S

Blends Q, R, and S, all modified with commercially available elastomers,
have properties that fall close to the line connecting the two squares in figure 1,
10 which represents the expected behavior. Blend P, an example of the present
invention, had the greatest impact improvement without a loss of strength, and as a
result falls well above the expected behavior line. This is a significant improvement
that will be magnified in blends with higher rubbery thermoplastic copolymer
content.

15

In summary, the instant blends provide impact resistance to PP without loss
of tensile strength, flex strength, or surface gloss as the commercial EP rubber
blends do. The instant blends provide this impact resistance even at below ambient
temperatures, in a temperature range that is commercially significant.

20

It is well known on the art that crosslinking of the rubber phase after it has
been dispersed in the semi-crystalline polymer can improve the toughness of the
blend. Crosslinking by peroxide cure treatment, E-beam treatment, or gamma
irradiation treatment acts to increase the molecular weight of the rubber phase and
25 prevent migration or aggregation of the rubber particles. In another embodiment of
this invention the alpha-olefin/cyclic olefin rubber phase of the blend is crosslinked,
preferably using a peroxide cure treatment to increase the molecular weight of the
rubber phase, and thereby the overall toughness of the PP blend. Typical peroxides
include di-cumyl peroxide and di-t-butyl peroxide.

30

- 20 -

EXAMPLE 3

11.6 g of PP4 was physically admixed with 11.6 g of ENB3 then poured into a preheated Brabender with 0.1201 g of di-t-butyl peroxide (98.5% pure). The components were blended for ten minutes at 190 C using a small 45 g mixing head. The cured blend was then tested for physical properties. The data for the cured blend, one uncured blend and neat polypropylene are summarized in Table 5.

Table 5. Strain Behavior of PP/Rubber Blends Before And After Peroxide Cure

Host Polymer MFR	Rubber ID Weight % Rubber	Approximate Young's Modulus (psi)	% Strain at Maximum Load	Energy-To-Break (lb-in)	Tensile Energy Absorption (lbs/in)
PP3 (35)	None 0%		12	20	100
PP3 (35)	ENB2 20%	78,600	9	5	31
PP4* (7.5)	ENB3 25%	71,700	404	132	802

* di-t-butyl peroxide

The data show that the rubbery thermoplastic copolymer will crosslink to improve the toughness of the blends to such an extent that they are competitive in properties with commercial reactor thermoplastic olefins. The instant blends are different however because the rubbery thermoplastic copolymer has a higher packing length than the semi-crystalline polymer causing it to be excluded from the surface. Packing length is defined and measured or calculated in Fetters, L. J., Lohse, D. J., Richter, D., Witten, T. A., and Zirkel, A. Macromolecules, 1994, incorporated by reference herein. After crosslinking the rubber phase the rubber particles remain excluded from the surface causing no loss of surface properties while increasing the toughness significantly. Evidence that the rubbery copolymer is excluded from the surface is provided by X-ray photoelectron spectroscopy (XPS)

- 21 -

which gave unperturbed, characteristic PP spectra before and after blending rubber, as well as before and after peroxide cure treatment.

As is apparent from the foregoing description, the materials prepared and the procedures followed relate to specific embodiments of the broad invention. It is apparent from the foregoing general description and the specific embodiments that, while certain forms of the invention have been illustrated and described, various modifications can be made without departing from the spirit and scope of this invention. Accordingly, it is not intended that the invention be limited thereby.

- 22 -

CLAIMS:

1. A blend comprising:
 - (1) semi-crystalline polymer, and
 - 5 (2) a rubbery thermoplastic copolymer comprising an α -olefin and from about 5 to about 30 mole% of cyclic olefin, said rubbery thermoplastic copolymer:
 - (a) having an Mw of at least about 30,000;
 - (b) being elastic over the range of temperatures between its Tg and about 100°C above its Tg; and
 - 10 (c) having a surface tension that is 5 dynes/cm or more different from the surface tension of the semi-crystalline polymer.
2. The blend of claim 1 wherein the α -olefin of the rubbery thermoplastic copolymer is ethylene.
- 15 3. The blend of claim 2 wherein the cyclic olefin is norbornene, substituted norbornene or isomers thereof.
- 20 4. The blend of claim 1 further comprising a peroxide.
5. The blend of any of claims 1-4 wherein the semi-crystalline polymer is isotactic polypropylene and the rubbery thermoplastic copolymer comprises ethylene and about 10 to about 30 mole % norbornene.
- 25 6. The blend of claim 5 wherein the propylene is present at about 99.5 to about 75 weight percent and the rubbery thermoplastic copolymer is present at about 0.5 to about 25 weight percent.
- 30 7. A molded article comprising a blend comprising: (1) about 75 to about 95.9 wt % of isotactic polypropylene;
 - (2) about 25 to about 0.5 wt% of a copolymer of ethylene and about 3 to about 30 mole % norbornene, said ethylene/norbornene copolymer being elastic over the range of temperatures between its Tg and about 100°C above its Tg and said copolymer having a surface tension that is 5 dynes/cm or more greater than the surface tension of the isotactic polypropylene; and
- 35


- 23 -

(3) optionally, a curing agent.

8. The article of claim 7 wherein the semicrystalline copolymer is polypropylene and the rubbery thermoplastic copolymer is a copolymer comprising ethylene and norbornene.
9. A process for producing a blend comprising physically admixing:
- (1) semi-crystalline polymer; with
 - (2) a rubbery thermoplastic copolymer of an α -olefin and from about 5 to about 30 mole% of cyclic olefin said rubbery thermoplastic copolymer:
 - (a) having an Mw of at least about 30,000;
 - (b) being elastic over the range of temperatures between its Tg and about 100°C above its Tg; and
 - (c) having a surface tension that is 3 dynes/cm or more greater than the surface tension of the semi-crystalline polymer.
10. The process of claim 9 wherein semi-crystalline copolymer is isotactic polypropylene and the rubbery thermoplastic copolymer is a copolymer of ethylene and about 10 to about 30 mole % norbornene.
11. A blend comprising semi-crystalline polypropylene and a copolymer having a surface tension at least 5 dynes or more greater than the surface tension of the semi-crystalline polypropylene comprising ethylene and about 5 to about 30 mole % norborne.

1/1

Flex Modulus vs. 23 °C Gardner Impact Results
E/NB vs. EP Modified Blends



INTERNATIONAL SEARCH REPORT

International Application No
PCT/US 95/13538

A. CLASSIFICATION OF SUBJECT MATTER
IPC 6 C08L23/10

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)
IPC 6 C08L C08F

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP,A,0 504 418 (IDEMITSU) 23 September 1992 see page 13, line 15 - page 14, line 22 see page 14, line 46 - page 15, line 21 see example 116 ---	1-11
X	DD,A,214 623 (VEB LEUNA WERKE "WALTER ULBRICHT") 17 October 1984 see page 4, line 15 - line 19 ---	1-11
X	EP,A,0 386 896 (MITSUI PETROCHEMICAL) 12 September 1990 see page 5, line 10 - page 25, line 11 -----	1-11

☐ Further documents are listed in the continuation of box C.

☒ Patent family members are listed in annex.

* Special categories of cited documents:

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

- *T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
- *X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
- *Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.
- *&* document member of the same patent family

Date of the actual completion of the international search

28 February 1996

Date of mailing of the international search report

21.03.96

Name and mailing address of the ISA

European Patent Office, P.B. 5818 Patentlaan 2
NL - 2280 HV Rijswijk
Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
Fax (+31-70) 340-3016

Authorized officer

Schmidt, H

INTERNATIONAL SEARCH REPORT

International Application No

PCT/US 95/13538

Patent document cited in search report	Publication date	Patent family member(s)	Publication date	
EP-A-504418	23-09-92	CA-A-	2070654	06-04-92
		WO-A-	9206123	16-04-92
		JP-A-	5262821	12-10-93
		JP-A-	5112621	07-05-93
		JP-A-	5132590	28-05-93
		JP-A-	5017527	26-01-93

DD-A-214623		NONE		

EP-A-386896	12-09-90	AT-T-	117706	15-02-95
		CA-A-	2009903	14-08-90
		DE-D-	69016227	09-03-95
		DE-T-	69016227	24-05-95
		JP-A-	2289636	29-11-90
		US-A-	4990559	05-02-91
